

0575

## QUADZERO™ NL

### fire-resistant, foil faced flexible noise barrier

Quadzero™ NL is a high-performance foil faced mass-loaded vinyl noise barrier, offering superior acoustic transmission loss and upgraded fire resistance.

With a fire-resistant foil facing, Quadzero™ NL was developed by Pyrotek® to meet stringent fire safety requirements in the marine, building and transport sectors. The product achieves the highest fire ratings complying with International Marine Organisation standards for low spread of flame, as well as international building and transportation standards for heat release, toxicity and flame propagation properties.

The upgraded fire safety provided by Quadzero™ NL is offered without reducing the strength, tear resistance or flexibility offered by the Wavebar® Quadzero™ product range.

Stiff lightweight panel constructions, such as plasterboard, drywall, plywood and hollow core doors, typically have coincidence dip resonance which allows noise to transmit through a construction. The coincidence dip is dependent on the material's stiffness and thickness and occurs at the point where the sound transmitted through the structure matches the natural frequency of the panel. Quadzero™ NL shifts the coincidence dip to frequencies limiting its impact, thereby maintaining the performance of the product.


The thin, dense mass barrier reflects and absorbs the energy, resulting in the reduction of transmission of sound through walls, ceilings and floors, therefore reducing the noise generated from sources such as mechanical equipment, engine noise and electronic devices.

#### VOC STATEMENT

Quadzero™ products contain no ozone-depleting substances and comply with European and Australian standards for Volatile Organic Compound emissions.

#### SPECIFICATIONS

Colour	Silver (Aluminium facing) White backing
Available	Standard roll size: 4.4 x 15 to 30 ft Barrier weight: 0.5 lb/ft <sup>2</sup> , 1 lb/ft <sup>2</sup> , 1.5 lb/ft <sup>2</sup> , 2 lb/ft <sup>2</sup> Custom sizes available depending on MOQ



### applications

- Applied in marine engine rooms & deckheads to reduce noise transmission
- Rail carriages for underfloor insulation to reduce track and brake noise
- Inside cavities or over lightweight wall, ceiling and floor constructions
- Around the outside of metal air ducts to reduce noise breakout
- Wrapped around noise emitting pipes, i.e. fluid or gas pulsation in chemical, petrochemical, LNG and wastewater treatment plants

### features

- Contains no ozone depleting substances
- Free from lead, unrefined odour-producing oils and bitumen
- Complies to IMO FTP 2010 - low spread of flame
- Multiple methods of installation accepted by USA Coast Guard (USCG)
- Complies to BS 476 Part 6 and 7 - Class 0
- Easy to cut, tape and mechanically fasten into position
- Self-extinguishes upon removal of the flame
- Resistant to water, oil and natural weather conditions
- Tear resistant with high tensile strength - ability to be suspended at lengths of up to 16.5 ft




**PRODUCT SPECIFICATIONS**

Barrier Weight	Thickness	Standard Roll Size	Standard Roll Weight	Ceiling Sound Transmission Test AMA-1-II-1967 (CSTC)	Operating temperature range
0.5 lb/ft <sup>2</sup>	0.05 in (1.2 mm)	4.4 ft x 30 ft (1.34 x 9.1 m)	66 lb (30 kg)	44 (Report No. A-22104-0228)	Continuous: -40 to 212 °F (-40 to 100 °C) Intermittent: -40 to 248 °F (-40 to 120 °C)
1 lb/ft <sup>2</sup>	0.1 in (2.5 mm)	4.4 ft x 30 ft (1.34 x 9.1 m)	132 lb (60 kg)	48 (Report No. -22107-0228)	
1.5 lb/ft <sup>2</sup>	0.15 in (3.7 mm)	4.4 ft x 20 ft (1.34 x 6.1 m)	132 lb (60 kg)	50 (Report No. 22114-0228)*	
2 lb/ft <sup>2</sup>	0.19 in (4.9 mm)	4.4 ft x 15 ft (1.34 x 4.6 m)	132 lb (60 kg)	-	

Tolerances: Length: -0/+2 in (50 mm), Width: -0/+0.2 in (5 mm), Thickness: ±0.02 in (0.5 mm), Weight: ±10% \* Tested to 1.64 lb/ft<sup>2</sup>.


Supplied untrimmed - means some surface coverings such as foils, film or fabric may overhang the ordered useable width

**MATERIAL PROPERTIES**

Test method	Property	Report no.	Results
IMO FTP Annex 1 Part 5	Surface flammability	377172	Complies for bulkheads, walls or ceiling linings and floors for 0.5 lb/ft <sup>2</sup> to 1.5 lb/ft <sup>2</sup> products  USCG Type approval granted
IMO FTP Annex 2	Smoke and toxicity	377172	
MED B	EC Type Certificate (Module B) for Marine Equipment Directive	MEDB0000750	
MED D	EC Type Certificate (Module D) for Marine Equipment Directive	MEDD000028J	
BS 476 Part 6	Fire propagation	377173, 377176	Complies with Class 0 for 1.2 lb/ft <sup>2</sup> to 2 lb/ft <sup>2</sup>
BS 476 Part 7	Surface spread of flame	377175, 377178	
ISO 1716	Heat of Combustion	348394	5311.6 KJ/Kg
GB8624 (EN 13501)	Fire classification of construction products and building materials	GN201312974	Class B (s2, d0, t0)
GB/T 20284 (EN 13823)	SBI - Single burning item test for building materials and products		
GB/T 8626 (ISO 11925-2)	Ignitability of building materials with direct flame impingement		
GB/T 20285	Toxic classification of fire effluents hazard for materials		
ASTM E84	Surface Burning Characteristics of Building Materials	01.17786.01.063a	Class A (Interior finishes), International Building Code up to 1 lb/ft <sup>2</sup>
CAN/ULC S102.2	Test for surface burning characteristics	104572841COQ-001B	FSI: 0, SDI: 15
GB/T 2406.1 & GB/T 2406.2	Burning behaviour by oxygen index	SZML110704163	31.5%
TB/T 3138	Specification of flame retardant materials for railway vehicle	SZML110704163	Complies
FMVSS 302	Flammability of interior materials	02313BD2	Complies to the requirements of US (DOT) Department of Transport for occupant compartments of motor vehicles

## ACOUSTIC PERFORMANCE

Frequency (Hz)	0.5 lb/ft <sup>2</sup>	1 lb/ft <sup>2</sup>	1.5 lb/ft <sup>2</sup>	2 lb/ft <sup>2</sup>
100	11	15	19	21
125	10	14	16	19
160	10	15	17	19
200	11	15	19	22
250	13	17	21	23
315	14	19	22	25
400	15	21	24	26
500	16	22	25	28
630	18	23	27	29
800	19	25	28	31
1000	21	27	30	33
1250	23	29	32	34
1600	25	31	34	36
2000	26	33	36	38
2500	28	34	37	40
3150	29	35	38	41
4000	31	37	40	43
5000	33	39	42	45
STC	21	26	30	32



Tested to ASTM E90 at Riverbank Acoustical Laboratories, USA  
Report Number: TL18-641, TL18-642, TL18-643 & TL18-644

## ISO 15665 PIPE INSULATION TESTING

Product	Test method	System Assembly	Report no.	Results
1 lb/ft <sup>2</sup>	ISO 15665 (Group 2 Pipe Size)	Available on request	A 3041-1E-RA-002	ISO 15665: Class A2 & B2 NORSOK R-004: Class 6 & Class 7
1 lb/ft <sup>2</sup> & 2 lb/ft <sup>2</sup>	ISO 15665 (Group 2 Pipe Size)	Available on request	A 3041-4E-RA-002	ISO 15665: Class B2 & C2 NORSOK R-004: Class 7 & Class 8

Testing was conducted using a system incorporating Wavebar®

For further information and contact details, please visit our website [pyroteknc.com](http://pyroteknc.com)

*Caveats: Specifications are subject to change without notice. The data in this document is typical of average values based on tests by independent laboratories or by the manufacturer and are indicative only. Materials must be tested under intended service conditions to determine their suitability for purpose. The conclusions drawn from acoustic test results are as interpreted by qualified independent testing authorities. Nothing here releases the purchaser/user from responsibility to determine the suitability of the product for their project needs. Always seek the opinion of your acoustic, mechanical and fire engineer on data presented by the manufacturer. Due to the wide variety of individual projects, Pyrotek is not responsible for differing outcomes from using their products. Pyrotek disclaims any liability for damages or consequential loss as a result of reliance solely on the information presented. No warranty is made that the use of this information or of the products, processes or equipment to which this Information Page refers will not infringe any third party's patents or rights. DISCLAIMER: This document is covered by Pyrotek standard Disclaimer, Warranty and © Copyright clauses. See [pyroteknc.com/disclaimer](http://pyroteknc.com/disclaimer).*

