# **Pyrotek**

INSTALLATION GUIDE

304-1IG

# WAVEBAR®

This Installation Guide provides recommendations for the application of Wavebar® to reduce crosstalk ceiling noise



### WORKING HEALTH AND SAFETY

• Personal Protection Equipment (PPE), including eye protection, gloves and safety clothing is recommended.

Note: This product is suitable for professional and experienced users only.

Pyrotek's Wavebar<sup>®</sup> reduces crosstalk ceiling noise dramatically. Refer to 'Wavebar<sup>®</sup> TDS-311IP' for more infromation

### DESCRIPTION

Wavebar® barriers are dense, flexible curtains that reflect noise. They are:

- more flexible, practical and economical than full height partitions
- improves confidentiality by virtually eliminating noise from adjacent rooms
- provides cross talk privacy and peace of mind in director's offices, board rooms
- consultation rooms, computer rooms, hallways, nurseries, etc.
- easy to install ideal for refurbishments. Simply suspend from slab to ceiling tiles, no additional framework is necessary.
- proven project history wavebar has been utilised in office fitouts and refurbishments for more than three decades as a safe and reliable way to reduce room-to-room noise transmitted via a common ceiling.



## applications

- Inside cavities or over lightweight wall, ceiling and floor constructions. Ideal for home theatre rooms, office partitions, meeting rooms
- Between the plenum chamber of a floor slab, the roof and adjoining partition walls
- Can be laminated onto lightweight structures to damp vibration and reduce airborne noise
- Portable acoustic curtains and screens (See Wavebar-Install-304-4/G for more information)

Please refer to our website pyroteknc.com for the latest information

# **Pyrotek**.

## WAVEBAR®





# **Pyrotek**.

**WAVEBAR®** 

## ACOUSTIC DATA

The following figures represent the tested room-to-room transmission loss achievable when wavebar is utilised in the ceiling plenum between the partition/ceiling and the slab.

- No Wavebar CAC = 35
- Wavebar 2 kg CAC = 44

- Wavebar 4 kg CAC = 48
  - Wavebar 8 kg CAC = 50



The above figures have been documented as a result of a testing program completed at an accredited laboratory.

Product	Roll width	Roll length	Roll diameter	Weight
wavebar 2 kg/m <sup>2</sup>		10 m		28 kg
wavebar 4 kg/m <sup>2</sup>	1380 mm	5 or 10 m	200 mm	28 - 56 kg
wavebar 8 kg/m <sup>2</sup>		5 m		52 kg

### **SPECIFICATIONS**

#### Material

The acoustic sound barrier shall be wavebar mineral loaded PVC as supplied by Pyrotek, comprising barium powder spread evenly throughout and encapsulated withing a flexible PVC sheet supported by a polyester fabric. The density shall be a minimum of 1.8g/cm<sup>3</sup>.

#### Performance

The wavebar barrier shall be 2 kg to achieve 44 CAC, 4 kg to achieve 48 CAC, 8 kg to achieve 50 CAC as documented by full test reports from an accredited laboratory.

#### Installation

The wavebar barrier shall be installed in strict accordance with the manufacturer's recommended procedures as detailed in this wavebar brochure. Care must be taken to seal around pipe or duct penetrations to eliminate sound leakage.

### Please contact Pyrotek<sup>®</sup> for further information or detailed advice on your specific application.

For further information and contact details, please visit our website pyroteknc.com Caveats: Specifications are subject to change without notice. The data in this document is typical of average values based on tests by independent laboratories or by the manufacturer and are indicative only. Materials must be tested under intended service conditions to determine their suitability for purpose. The conclusions drawn from acoustic test results are as interpreted by qualified independent testing authonities. Nothing here releases the purchaser/user from responsibility to determine the suitability of the product for their project needs. Always seek the opinion of your acoustic, mechanical and fine engineer on data presented by the manufacturer. Due to the wide variety of individual projects. Pyrotek is not responsibile for differing outcomes from using their products. Pyrotek disclaims any liability for damages or consequential loss as a result of reliance solely on the information presented. No warranty is made that the use of this information or of the products, processes or equipment to which this Information Page refers will not infining any third party's patents or rights. DISCLAIMER: This document is covered by Pyrotek standard Disclaimer, Warranty and © Copyright clauses. See pyrotek.ccom/disclaimer.



DNVG

Page 3 of 3 NOV-16-EN-304-1IG