

## QUADZERO™ dBX

# dBX flexible noise barrier with aluminium glass-cloth facing

Quadzero dBX is a high-performance noise control product that exhibits superior transmission loss performance. It features a flexible, mass-loaded noise barrier, laminated with an aluminium foil-covered glass-cloth facing (AGC). It was developed to meet market requirements in marine, rail, domestic, commercial, industrial and automotive industries.

Quadzero dBX is a thin, strong, flexible mass barrier made from recycled polymers that are halogen-free and offered in a range of weights that provide effective acoustic transmission loss performance. The aluminium glass cloth (AGC) face offers a durable flame-retardant surface, complying to IMO FTP Code.

Stiff lightweight panel constructions, such as plasterboard, drywall, plywood and hollow core walls, typically have coincidence dip resonance which allows noise to transmit through a construction. Quadzero dBX shifts the coincidence dip to frequencies limiting its impact, thereby maintaining the performance of the product.

The dense, mass barrier attenuates noise from mechanical equipment, engine, and electronic audio technologies such as radio and television, when transmitted through walls, ceilings and floors.

#### **VOC STATEMENT**

Quadzero<sup>™</sup> products contain no ozone-depleting substances and comply with European and Australian standards for Volatile Organic Compound emissions.

#### **SPECIFICATIONS**

Colour	Silver (Aluminium face)
Available	Standard Sizes 1.35 x 10 m (4.4 ft x 32.8 ft) 1.35 x 5 m (4.4 ft x 16.4 ft) 1.4 x 1 m (4.6 x 3.3 ft)
	Custom rolls or sheets available depending on MOQ



# applications

- Marine engine rooms and deckheads to reduce noise transmission
- Rail carriages for under-floor insulation to reduce track and braking noise
- Automotive cabin application to reduce engine and road noise transmitting through the structure
- Inside cavities or over lightweight wall, ceiling and floor constructions
- Ideal for theatres, office partitions, meeting rooms and high privacy areas
- · Usable where moulded parts or components are required

### features

- Complies with IMO FTP (low spread of flame) and EN45545-2 (for rail applications)
- · Resistant to water, oil and natural weather conditions
- Free from lead, odour-producing oils, halogens and bitumen
- No ozone-depleting substances generated during manufacture
- · Tear-resistant with high tensile strength
- Simple to cut, tape and mechanically fasten into position
- Available with various laminates such as fabrics, foams and polyester fibre









### PRODUCT SPECIFICATIONS

Barrier weight	Thickness	Product Dimensions	Product Weight	Operating temperature range*
2 kg/m² (0.4 lb/ft²)	1.5 mm (0.059 in)	1.35 x 10 m (4.4 ft x 32.8 ft)	27 kg (60 lb)	Continuous: -50 to 70 °C (-58 to 158 °F) Intermittent: -50 to 90 °C (-58 to 194 °F)
4 kg/m² (0.8 lb/ft²)	2.5 mm (0.098 in)	1.35 x 10 m (4.4 ft x 32.8 ft)	54 kg (119 lb)	
8 kg/m² (1.6 lb/ft²)	4.5 mm (0.177 in)	1.35 x 5 m (4.4 ft x 16.4 ft)	54 kg (119 lb)	
10 kg/m2 (2 lb/ft2)	5.5 mm (0.217 ln)	1.4 x 1 m (4.6 x 3.3 ft)	14 kg (31 lb)	

 $To lerances: Length: \pm 1\%, \textit{Width: -0/+5} \; mm \; (0.2 \; in), \textit{Thickness: } \pm 15\%, \textit{Weight: } \pm 0.5 \; kg/m^2 \; (0.1 \; lb/ft^2)$ 

Additional barrier weights available depending on MOQ

### **MATERIAL PROPERTIES**

Test method	Property	Report no.	Result	
IMO FTP Annex 1 Part 5	Surface flammability	201222 277177		
IMO FTP Annex 2	Smoke and toxicity	381223, 377177	Complies for bulkheads, walls or ceiling linings and floors for 2 - 8 kg/m <sup>2</sup>	
MED B	EC Type Certificate (Module B) for Marine Equipment Directive	MEDB000074V		
MED D	EC Type Certificate (Module D) for Marine Equipment Directive	MEDD000028J		
EN 45545-2 (ISO 5658-2)	Spread of flame			
EN 45545 -2 (EN 17084 (1) : 50 kWm <sup>-2</sup> )	Gas Toxicity	0096-22-F	R1 R7 (HL1, HL2, HL3) For 2kg to 10kg products	
EN 45545-2 (ISO 5659-2: 50 kWm <sup>-2</sup> )	Heat release rate by cone calorimeter	0090-22-1		
EN 45545-2 (ISO 5660-1: 50 kWm <sup>-2</sup> )	Smoke generation (optical density)			
ASTM E162	Surface flammability	102087697MID-001Rev2	Complies for US (FRA) Federal railroad administration requirements and requirements of NFPA 130	
ASTM E662	Optical density of smoke generated	102087697MID-002Rev2		
ASTM E800 (SMP-800C)	Gases present or generated during fires 102087697MID-003Rev2		Complies for US (DOT) Department of Transportation requirements for acoustic insulation of transit bus and vans (Docket 90A)	
Gost 12.1.044-89	Occupational safety standards system. Fire and explosion hazard of substances and materials	001610	Complies	



<sup>\*</sup>Temperatures -50 to -20 require material to be supported on rigid surface



### **ACOUSTIC PERFORMANCE**

Frequency (Hz)	2 kg/m²	4 kg/m²	8 kg/m²	10 kg/m²
100	3.8	6.7	13.3	18.9
125	6.4	10.8	16.2	19.3
160	10.2	14.7	22.6	22.6
200	9.8	14.1	20.5	23.4
250	12.0	16.0	22.3	25.2
315	13.2	17.9	23.2	26.1
400	14.8	19.7	25.0	28.1
500	15.8	20.6	26.0	29.3
630	17.8	22.6	28.6	30.5
800	20.0	25.0	30.1	32.3
1000	21.7	26.6	32.7	34.9
1250	22.7	27.6	33.4	35.7
1600	23.9	28.5	34.1	36.4
2000	25.6	30.4	35.9	38.4
2500	27.7	32.1	37.6	40.4
3150	29.9	34.3	39.7	42.7
4000	32.2	36.7	42.1	45.7
5000	34.6	39.0	45.0	48.7
Rw	21	25	31	34
STC	21	26	31	34





For further information and contact details, please visit our website pyroteknc.com





